



(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication of patent specification :
02.03.94 Bulletin 94/09

(51) Int. Cl.⁶ : **A61K 9/00, A61K 9/52,
A61K 9/70, A61K 47/30**

(21) Application number : **91114374.1**

(22) Date of filing : **27.08.91**

(54) **Controlled drug release composition.**

(30) Priority : **30.08.90 JP 229887/90**

(43) Date of publication of application :
11.03.92 Bulletin 92/11

(45) Publication of the grant of the patent :
02.03.94 Bulletin 94/09

(84) Designated Contracting States :
AT BE CH DE DK ES FR GB GR IT LI LU NL SE

(56) References cited :
**EP-A- 0 204 476
EP-A- 0 245 820
WO-A-78/00011
US-A- 4 048 256**

(73) Proprietor : **Senju Pharmaceutical Co., Ltd.**
5-8, Hiranomachi 2-chome, Chuo-Ku
Osaka-shi, Osaka 541 (JP)

(72) Inventor : **Morita, Yasushi**
6-10-305, Nishimidorigaoka 2-chome
Toyonaka-shi, Osaka 560 (JP)
Inventor : **Ohtori, Akira**
Cityvale New Izuka 106, 499-1, Ohazaikisu
Iizuka-shi, Fukuoka 820 (JP)
Inventor : **Andoh, Masako**
Cube Mukogawa V-205, 11-24, Muko-cho
3-chome
Amagasaki-shi, Hyogo 661 (JP)

(74) Representative : **von Kreisler, Alek,**
Dipl.-Chem. et al
Patentanwälte von Kreisler-Selting-Werner
Postfach 10 22 41
D-50462 Köln (DE)

EP 0 474 098 B1

Note : Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

Description**BACKGROUND OF THE INVENTION****1. Field of the Invention**

The present invention relates to a composition comprising a hardly soluble drug, a water-soluble macromolecular compound and a biodegradable macromolecular compound, and as such insuring increased solubility and well controlled release of said hardly soluble drug.

2. Description of Prior Art

It is known that in the administration of a hardly soluble drug, the rate of dissolution of the drug is determinant of the rate of absorption of the drug in many instances and that the solubility of the drug has a profound influence on the bioavailability of the drug. A diversity of methods have been proposed for enhancing the dissolution rate of hardly soluble drugs. There are reports, for instance, on the preparation of a coprecipitate between a hardly soluble drug and a highly water-soluble macromolecular substance such as polyvinylpyrrolidone and the use of the coprecipitate as an oral medicine [Shotaro Sakurai et al.: The Archives of Practical Pharmacy, 47, 191-196 (1987) or a suppository (Yoshiko Hamamoto et al.: The Archives of Practical Pharmacy, 49, 209-214 (1989)).

EP-A-0 245 820 relates to a method for preparing biodegradable microspheres for the controlled release of active agents whereby the drug delivery system comprises a water-soluble polymeric structure and a biologically active macromolecular agent.

It is true that the dissolution of the hardly soluble drug from such a coprecipitate prepared by these prior art technologies is rapid indeed but the rate of release of the drug can hardly be controlled. Therefore, there are defects that it is impossible to supply the recipient body with a sufficient amount of the drug to maintain a therapeutically effective concentration and thus its sufficient efficacy cannot be expected. Moreover, the risk has been pointed out that the rate of release may sometimes be so rapid that more than the necessary amount of the drug is released at a time to cause adverse reactions.

Under the circumstances the development of a therapeutic system (composition) insuring enhanced solubility and controlled release of a hardly soluble drug has been keenly demanded in the pharmaceutical field.

Accordingly, in view of these circumstances, the inventors of the present invention explored this field of technology with due diligence for establishing a composition which would be free from the above-mentioned disadvantages and capable of insuring enhanced solubility and well controlled release of a hardly soluble drug and discovered that these requirements can be met by providing a composition comprising a hardly soluble drug, a water-soluble macromolecular compound and a biodegradable macromolecular compound. This finding was followed by further research, which has culminated in the present invention.

SUMMARY OF THE INVENTION

The present invention is, therefore, concerned with a controlled drug release composition comprising a composition comprising a steroidal compound, a water-soluble macromolecular compound selected from polyvinylpyrrolidone, polyethylene glycol and hydroxypropylcellulose and a biodegradable macromolecular compound selected from polylactic acid and polyglycolic acid and the corresponding copolymers, which composition can be freely tailored to the required solubility and release pattern of the steroidal compound through adjustment of the ratio of said ingredients.

DETAILED DESCRIPTION OF THE INVENTION

The steroidal compound which can be used in the composition of the invention includes, *inter alia*, various steroidal compounds such as hydrocortisone, hydrocortisone acetate, dexamethasone, fluorometholone and so on.

The water-soluble macromolecular compound which is used in the composition of the invention is selected from polyvinylpyrrolidone, polyethylene glycol, and hydroxypropylcellulose. The average molecular weight of the water-soluble macromolecular compound to be used for the invention is generally in the range of about 5,000 to about 5,000,000, preferably from about 10,000 to about 1,000,000, according to the intended release pattern of the hardly soluble compound and so on. These compounds can be employed singly or in a suitable combination according to the intended application.

The biodegradable macromolecular compound which is used in the composition of the invention is a high molecular weight compound which is physiologically acceptable and decomposes in the body and absorbed and is selected from polylactic acid and polyglycolic acid, inclusive of the corresponding copolymers. The average molecular weight of the biodegradable macromolecular compound to be used for the invention is generally in the range of about 200 to about 100,000, preferably from about 1,000 to about 10,000, according to the intended release pattern of the hardly soluble compound and so on.

The composition of the present invention can be manufactured by the solid dispersion method (W. L. Chiou et al., J. Pharm. Sci., 60, 1281 (1971) which is commonly employed. However, it is preferable to employ the solvent evaporation method which comprises dissolving uniformly a steroidal compound a water-soluble macromolecular compound and a biodegradable macromolecular compound in an organic solvent and removing the solvent by evaporation. The organic solvent to be used in such solvent evaporation method may be virtually any solvent that is capable of dissolving the steroidal compound water-soluble macromolecular compound and biodegradable macromolecular compound and, at the same time, can be easily distilled off. Particularly preferred examples are ethanol, acetonitrile, acetone and chloroform. These solvents can be used either singly or in an appropriate combination according to the intended application.

In preparing the composition of the invention, the formulating ratio of the steroidal compound, water-soluble macromolecular compound and biodegradable macromolecular compound can be freely selected according to the desired rate of release of the steroidal compound. While this formulating ratio should vary with different species of compounds used and the contemplated method of administration, it is generally recommended to use about 1-10 weight parts of the water-soluble macromolecular compound and about 1 to 10 weight parts of the biodegradable macromolecular compound per weight part of the steroidal compound. The more preferred proportions are about 3 to 5 weight parts of the water-soluble macromolecular compound and about 1 to 3 weight parts of the biodegradable macromolecular compound per weight part of the steroidal compound.

The composition of the present invention, which is thus available upon removal of the organic solvent, can be used as it is. However, according to the intended application such as the indicated site of action of the drug, the composition can be further processed, with great ease, into such dosage forms as the disk, rod, film, sheet, microcapsule and so on. By way of example, such a dosage form can be easily prepared by dissolving the steroidal compound, water-soluble macromolecular compound and biodegradable macromolecular compound in an organic solvent, removing the solvent by evaporation, drying the residue under reduced pressure, pulverizing the dry residue and molding the resulting powder into a disk, rod or the like in the conventional manner. In the case of a rod, the above pulverized residue can also be molded by the pressure-heat melting method. A film or sheet can be manufactured by dissolving the same in an organic solvent and casting the solution. If desired, a film or a microcapsule can be manufactured by the conventional technology in the course of removal of the solvent. For example, microcapsules can be manufactured by the so-called in-liquid drying method which comprises dispersing an organic solvent solution of the three ingredients in cottonseed oil, castor oil or the like and removing the solvent by distillation.

The composition of the invention can thus be used in a variety of dosage forms and such preparations can be selectively applied to indicated sites, such as the skin, eye, ear, nose, oral cavity or vagina, according to diseases, or orally for the treatment of systemic diseases.

Unless contrary to the objects of the invention, the composition of the present invention can be formulated with excipients which are commonly incorporated in various pharmaceutical preparations.

Compared with the conventional composition comprising a hardly soluble drug and a water-soluble macromolecular compound, the composition of the present invention not only insures a remarkably increased solubility of the drug but also a tailored release of the drug, besides being moldable into a variety of dosage forms, thus being an excellent composition.

EXAMPLE

The following examples are further illustrative of the present invention.

[Example 1] Solubility testing of hydrocortisone acetate compositions

Hydrocortisone acetate (HCA), polyvinylpyrrolidone (PVP) [average molecular weight: 40,000] and polylactic acid (PLA) [average molecular weight: 6,000] were mixed according to the formulas shown below and each mixture was dissolved in 50 ml of acetonitrile. The acetonitrile was gradually distilled off under reduced pressure at about 60°C and the residue was dried in vacuo at room temperature for 16 hours to give a hydrocortisone acetate composition.

5	No.	Hydrocortisone acetate	Polyvinyl- pyrrolidone	Polylactic acid
10	1	0.1 g	0.1 g	-
	2	0.1 g	0.5 g	-
	3	0.1 g	1.0 g	-
15	4	0.1 g	-	0.1 g
	5	0.1 g	0.1 g	0.1 g
20	6	0.1 g	0.1 g	0.3 g
	7	0.1 g	0.3 g	0.1 g
25	8	0.1 g	0.5 g	0.3 g

30

Each of the hydrocortisone acetate compositions thus prepared was added to 50 ml of 1/150 M phosphate buffer (pH 7.2) to provide to a test sample containing about 5 mg of hydrocortisone acetate and the solubility of hydrocortisone acetate at 37°C was determined.

As shown in Fig. 1, the HCA-polyvinylpyrrolidone compositions gave solubility values about two- to three-fold the solubility of the active drug used alone. On the other hand, as shown in Fig. 2, the compositions of the invention, which contained both polyvinylpyrrolidone and polylactic acid, gave remarkably higher solubilities, e.g. in the case of composition No. 8 more than about six-fold as high after 60 minutes.

40 [Example 2] Solubility testing of hydrocortisone, dexamethasone and fluorometholone compositions

40

In 50 ml of ethanol-acetonitrile (4/1) were dissolved 0.1 g of hydrocortisone (HC), dexamethasone (DM) or fluorometholone (FLU), 0.5 g of polyvinylpyrrolidone [average molecular weight: 40,000] and 0.3 g of polylactic acid [average molecular weight: 2,000] and the solution was processed into a composition in the same manner as Example 1.

Each of the three steroid compositions thus prepared was added to 50 ml of 1/150 M phosphate buffer (pH 7.2) to provide a sample containing about 5 ml of the steroid and the solubility of the drug at 37°C was evaluated.

The results are shown in Fig. 3. After 60 minutes, the solubility of the steroid drug was increased by 1.4-fold in the case of the hydrocortisone composition, 1.7-fold in the case of the dexamethasone composition and 5.2-fold in the fluorometholone composition.

50

[Example 3] Solubility testing of hydrocortisone acetate compositions

In 50 ml of ethanol-acetonitrile (1/4) were dissolved 0.1 g of hydrocortisone acetate, 0.5 g of polyvinylpyrrolidone [average molecular weight: 40,000], polyethylene glycol [average molecular weight: 4,000] or hydroxypropylcellulose [average molecular weight: 60,000], and 0.3 g of polylactic acid [average molecular weight: 4,000] and the solubility of the steroid was determined as in Example 2.

55

The results were similar to those obtained in Example 2.

[Example 4] Solubility testing of hydrocortisone, dexamethasone and fluorometholone compositions

The same amounts of the same ingredients as used in Example 2 were respectively dissolved in chloroform or acetone-acetonitrile (1/4) and the solutions were processed into compositions as in Example 1. These compositions gave solubility results similar to those described above.

[Example 5] Release testing of hydrocortisone, acetate composition

The hydrocortisone acetate composition (No. 8) prepared in Example 1 was filled into a Teflon tube having an inside diameter of 0.8 mm and pushed with a stainless steel push-rod from either end at about 80°C to give a rod having a diameter of 0.8 mm and a length of 5 mm.

This rod was immersed and shaken in 100 ml of 1/150 M phosphate buffer (pH 7.2) at 37°C to evaluate the time course of release.

As shown in Fig. 4, the release followed the 0-order pattern. It was found that the release of the drug from the rod molded from a binary mixture of the hydrocortisone acetate and polylactic acid [average molecular weight: 2,000] in the same manner as Example 5 was much retarded as compared with the release from the rod molded from the composition (No. 8).

[Example 6] Microcapsule

The same amounts of the same ingredients as used in Example 2 were respectively dissolved in 30 ml of ethanol-acetonitrile (2:1) and each solution was added dropwise to 100 ml of cottonseed oil containing 2 g of soybean lecithin under constant stirring at 1,500 rpm. The mixture was further stirred at about 65°C for 6 hours. The mixture was then centrifuged at 5,000 rpm for 10 minutes, washed with hexane and dried in vacuo at room temperature for 16 hours to give microcapsule sized about 1 μ m.

[Example 7] Film

The same amounts of the same ingredients as used in Example 2 were respectively dissolved in 50 ml of acetone-acetonitrile (9:1) and each solution was cast in a Teflon vessel and dried at room temperature to provide a sheet.

This sheet was then calendered to give a film having a thickness of about 600 μ m.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a diagram showing the solubility of hydrocortisone acetate-polyvinylpyrrolidone compositions, where the ordinate represents solubility and the abscissa represents time (minutes).

Fig. 2 is a diagram showing the solubilities of a hydrocortisone acetate-polyvinylpyrrolidone-poly-lactic acid compositions, where the ordinate represents solubility and the abscissa represents time (minutes).

Fig. 3 is a diagram showing the solubility of a hydrocortisone/dexamethasone/ or fluorometholone-polyvinylpyrrolidone-poly-lactic acid composition, where the ordinate represents solubility and the abscissa represents time (minutes).

Fig. 4 shows the pattern of release from a hydrocortisone acetate-polyvinylpyrrolidone-poly-lactic acid rod, where the ordinate represents the % residue of hydrocortisone acetate in the rod and the abscissa represents time (days).

Claims

Claims for the following Contracting States : AT, BE, CH, LI, DE, DK, FR, GB, IT, LU, NL, SE

1. A composition comprising a steroidal compound, a water-soluble macromolecular compound selected from polyvinylpyrrolidone, polyethylene glycol and hydroxypropylcellulose and a biodegradable macromolecular compound selected from polylactic acid and polyglycolic acid and the corresponding copolymers.
2. A composition according to claim 1 which is in the dosage form of a rod, sheet, film, disk or microcapsule.

Claims for the following Contracting States : ES, GR

- 5 1. Process for preparing a controlled drug release composition comprising dissolving uniformly a steroidal compound, a water-soluble macromolecular compound selected from polyvinylpyrrolidone, polyethylene glycol and hydroxypropylcellulose and a biodegradable macromolecular compound selected from polylactic acid and polyglycolic acid and the corresponding copolymers in an organic solvent and removing the solvent by evaporation.
- 10 2. Process according to claim 1 wherein the composition is in the dosage form of a rod, sheet, film, disk or microcapsule.

Patentansprüche

15 **Patentansprüche für folgende Vertragsstaaten : AT, BE, CH, LI, DE, DK, FR, GB, IT, LU, NL, SE**

- 20 1. Zusammensetzung, umfassend eine steriode Verbindung, eine aus Polyvinylpyrrolidon, Polyethylenglycol und Hydroxypropylcellulose ausgewählte wasserlösliche makromolekulare Verbindung und eine aus Polymilchsäure und Polyglycolsäure und den entsprechenden Copolymeren ausgewählte, biologisch abbaubare makromolekulare Verbindung.
2. Zusammensetzung nach Anspruch 1, die in der Dosierungsform eines Stabes, einer Folie, eines Films, einer Scheibe oder einer Mikrokapsel vorliegt.

25 **Patentansprüche für folgende Vertragsstaaten : ES, GR**

- 30 1. Verfahren zur Herstellung einer Zusammensetzung für die gesteuerte Freisetzung eines Medikaments, umfassend das gleichmäßige Auflösen einer steroiden Verbindung, einer aus Polyvinylpyrrolidon, Polyethylenglycol und Hydroxypropylcellulose ausgewählten wasserlöslichen makromolekularen Verbindung und einer aus Polymilchsäure und Polyglycolsäure und den entsprechenden Copolymeren ausgewählten, biologisch abbaubaren makromolekularen Verbindung in einem organischen Lösungsmittel und das Entfernen des Lösungsmittels durch Abdampfen.
- 35 2. Verfahren nach Anspruch 1, worin die Zusammensetzung in der Dosierungsform eines Stabes, einer Folie, eines Films, einer Scheibe oder einer Mikrokapsel vorliegt.

Revendications

40 **Revendications pour les Etats contractants suivants : AT, BE, CH, LI, DE, DK, FR, GB, IT, LU, NL, SE**

- 45 1. Composition comprenant un composé stéroïdien, un composé macromoléculaire hydrosoluble choisi parmi la polyvinylpyrrolidone, le polyéthylèneglycol et l'hydroxypropylcellulose, et un composé macromoléculaire biodégradable choisi parmi le poly(acide lactique) et le poly(acide glycolique), et les copolymères correspondants.
2. Composition selon la revendication 1, dont la forme posologique se présente sous forme d'une baguette, d'une feuille, d'un film ou d'une microcapsule.

50

Revendications pour les Etats contractants suivants : ES, GR

- 55 1. Procédé pour préparer une composition assurant la libération retardée d'un médicament, qui consiste à dissoudre uniformément dans un solvant organique ou composé stéroïdien, un composé macromoléculaire hydrosoluble choisi parmi la polyvinylpyrrolidone, le polyéthylèneglycol et l'hydroxypropylcellulose, et un composé macromoléculaire biodégradable choisi parmi le poly(acide lactique) et le poly(acide glycolique), et les copolymères correspondants, et à éliminer le solvant par évaporation.

- 2.** Procédé selon la revendication 1, dans lequel la forme posologique de la composition se présente sous forme d'une baguette, d'une feuille, d'un film, d'un disque ou d'une microcapsule.

5

10

15

20

25

30

35

40

45

50

55







